



# Product Guideline No.3

*Factory-made extruded polystyrene products*

Revision index	Date of implementation
B	01/04/2024



## Table of contents

---

<b>1</b>	<b>PURPOSE .....</b>	<b>1</b>
<b>2</b>	<b>ADDITIONAL ELEMENTS OF THE CERTIFICATE APPLICATION TECHNICAL FILE .....</b>	<b>1</b>
<b>3</b>	<b>CHARACTERISTICS WHICH CAN BE CERTIFIED .....</b>	<b>1</b>
<b>4</b>	<b>METHODS OF DETERMINATION OF THE CERTIFIED CHARACTERISTICS BY THE PILOT LABORATORIES ..</b>	<b>1</b>
4.1	THERMAL CONDUCTIVITY .....	1
4.2	THERMAL RESISTANCE .....	1
4.3	REACTION TO FIRE .....	2
4.4	SERVICE COMPRESSION STRENGTH, NORMAL SERVICE DEFORMATION.....	2
4.5	CLASS OF INSULATING UNDERLAYERS BENEATH SCREED OR FLOATING SLAB AND UNDER TILES .....	2
4.6	EMISSION .....	2
4.7	SPECIFIC HEAT CAPACITY .....	2
<b>5</b>	<b>FACTORY PRODUCTION CONTROL .....</b>	<b>3</b>
5.1	THICKNESS, LENGTH, WIDTH AND DENSITY .....	3
5.2	COMPRESSION RESISTANCE .....	4
5.3	DIMENSIONAL STABILITY .....	4
5.4	COHESION .....	4
5.5	WATER VAPOUR PERMEABILITY .....	4
<b>6</b>	<b>TESTS PERFORMED DURING FOLLOW-UP.....</b>	<b>5</b>
<b>7</b>	<b>CERTIFICATE MAINTENANCE RULES .....</b>	<b>6</b>
<b>8</b>	<b>MARKING RULES .....</b>	<b>6</b>



## **1 Purpose**

---

This Product Guideline supplements the measures in the General Guidelines.

This Product Guideline concerns panels and rolls of extruded polystyrene, in accordance with harmonised European standard NF EN 13164.

## **2 Additional elements of the certificate application technical file**

---

The technical file defined in paragraph 2.2 of the General Guidelines does not require any additional elements.

## **3 Characteristics which can be certified**

---

The characteristics which can be certified are the characteristics listed in paragraph 4 of standard NF EN 13164, supplemented by the following characteristics:

- Service compression strength, normal service deformation
- Class of insulating underlayers beneath screed or floating slab and under tiles
- Emissivity
- Specific heat capacity

## **4 Methods of determination of the certified characteristics by the pilot laboratories**

---

The test methods applied by the pilot laboratory for each of the characteristics are defined in paragraph 5 of standard NF EN 13164, supplemented by the following measures.

### **4.1 Thermal conductivity**

The measures of paragraph 1.1 of Technical Specification No.1 apply.

### **4.2 Thermal resistance**

Certified thermal resistance is defined according to the procedures in Technical Specification No.2.



### **4.3 Reaction to fire**

The measures in Technical Specification No.3 apply.

### **4.4 Service compression strength, normal service deformation**

The measures in Technical Specification No.5 apply.

### **4.5 Class of insulating underlayers beneath screed or floating slab and under tiles**

If the floor classification is certified, the conditions of Technical Specification No.6 apply.

### **4.6 Emissivity**

If the product has a surface coating for which the emissivity is certified, the procedures in Technical Specification No.7 apply.

### **4.7 Specific heat capacity**

The measures in Technical Specification No.10 apply.



## 5 Factory production control

---

Production control in the production unit satisfies the requirements of appendix B of European standard NF EN 13164.

In addition to these measures, for the following certified characteristics for the purposes of these regulations and described in detail in the various Technical Specifications, the procedures (methods and minimum test frequencies) provided for in this Technical Specification apply:

- Reaction to fire
- Service compression strength and normal service deformation
- Class of insulating underlayers beneath screed or floating slab and under tiles
- Emissivity
- Specific heat capacity

In addition, the following specific measures must be complied with.

### 5.1 Thickness, length, width and density

The thickness, length, width and density are checked on each product, each thickness and each type of facing once after adjusting the machine and once after each batch of a maximum of 250 m<sup>3</sup>. In the case of small production runs (< 250 m<sup>3</sup>), the controls shall be performed on each product at least once after adjusting the machine.

The thickness measurements are made in accordance with standard NF EN 823 (or by any other method leading to the same results) in line with the following minimum provisions:

- measuring equipment: the accuracy of the instrument used must be compatible with the stated thickness tolerances. The tape measure should be avoided as the sole means of measurement for thickness controls.
- sampling: the measurements are made on a slab of actual size or having a minimum length of 1 m. If it is impossible to measure such dimensions, the minimum dimensions may be reduced, with the agreement of the lead member, based on specific proof that the sample for thickness measurements is representative.
- measuring plan: the thickness is measured according to the measurement plan in standard NF EN 823, at a minimum of 4 points, 3 of which are distributed along the edges of the slab and 1 in the centre, where required (this measurement may be obtained after cutting the sample in two). Based on specific proof that the thickness at the edges and in the centre of the slabs is uniform, the thickness checks may be made on the edges of the slab only. Thickness in the centre of the slab shall be verified periodically (e.g. during the follow-up audits).

The lengths and widths are measured in accordance with standard NF EN 822 complying at least with the measuring plan indicated. These measurements are made on the real-scale product (slab) using a tape measure.



The density is determined in accordance with standard NF EN 1602 based on the dimensional measurements defined above. This measurement can be made including the facings, the weight of which being then deducted from the result. However it is necessary to cross-check periodically on products from which the facing has been removed.

## 5.2 Compression resistance

Levels I1, I2 and I3: no tests for products having a density greater than 30 kg/m<sup>3</sup> and a thickness less than or equal to 120 mm.

Levels I4 and I5: periodic check according to the test defined by test method 75-301, the frequency of which is defined according to the difference between the test results and the certified level.

## 5.3 Dimensional stability

A period of stabilisation is generally required. This period depends on the product and the certified level. Consequently, the dates of manufacture must appear on the products.

## 5.4 Cohesion

For products having a cohesion at least twice that of the certified level, no test is required. If this is not the case, a periodical control must be performed concerning either cohesion or bending.

The frequency of testing varies according to the products and is in general at least once every 24 hours.

For multi-layer products, the control is performed on the assembled product.

## 5.5 Water vapour permeability

Tests may be necessary when satisfaction of the certified level of permeability depends on the quality of one or more coatings. In this case, the tests concern either the coating or the coated product. The frequency of these tests depends on the nature of the coating and the difference between the results of the tests and the certified level.



## 6 Tests performed during follow-up

For characteristics requiring monitoring, random tests are conducted at least once a year according to the table below when relevant to the product in question.

The tests are conducted in accordance with the measures in European standard NF EN 13164, supplemented if applicable by the procedures described in the Technical Specifications corresponding to the characteristics tested.

Characteristics (NF EN 13164)	Test methods	Place of performance of the tests
Thermal resistance – Thermal conductivity	NF EN 12667 NF EN 12939	Pilot laboratory
Length and width	NF EN 822	Production unit and pilot laboratory
Thickness	NF EN 823 or NF EN 12431	Production unit and pilot laboratory
Squaring	NF EN 824	Production unit
Flatness	NF EN 825	Production unit
Reaction to fire <sup>1</sup>	NF EN 13501-1	Pilot laboratory
Other characteristics or criteria	Test methods	Place of performance of the tests
Emissivity	Technical Specification No.7	Pilot laboratory
Density	NF EN 1602	Pilot laboratory
Service resistance (R <sub>CS</sub> )	Technical Specification No.5	Production unit and pilot laboratory
Dimensional stability (Is a "Use" is applicable)	Technical Specification No.11, §3.3, cycles from 23 to 60°C (DTU 45.4 P1-2, Tab.3 §3.3.3)	Pilot laboratory

The certifying body may also perform tests to verify other characteristics not listed in the table below, in particular if there is any doubt as to the compliance of the certified values.

Random testing is performed for reaction to fire in the case of products coming under conformity certificate system 1 for CE marking, in the case of the Keymark or at the manufacturer's request. In addition, for the follow-up tests, the following measures apply: one

<sup>1</sup> The reaction to fire classification is monitored by conducting random tests once every two years.



SBI test for each expansion agent on the worst case according to the initial type testing (class C).

## 7 Certificate maintenance rules

---

The certificate maintenance rules are defined in paragraph 4 of the General Guidelines.

Based on the results of the tests performed by the pilot body, product compliance is verified:

- For the dimensional characteristics according to the requirements of paragraph 4 of European standard NF EN 13164;
- For the thermal performance according to paragraphs 2.1 or 2.2 of Technical Specification E;
- For the following characteristics certified under these regulations and described in detail in the various Technical Specifications, according to the conditions stipulated in these Technical Specifications:
  - Reaction to fire
  - Service compression strength and normal service deformation
  - Emissivity

## 8 Marking Rules

---

The marking rules laid out in Technical Specification D apply.

In particular, the information label complies with the measures in paragraph 3.1.1 of this Technical Specification.